

**AMENDMENTS TO THE SPECIFICATION:**

Please replace Table 1 on page 6 with the following table:

Table 1. Shrinkage Ratios of SOG Layers

Types of low-dielectric layer	Shrinkage ratio (%)	Temperature (°C)	Time
Silicate (Inorganic SOG)	12-14	425, 900	1 hr
Phosphosilicate (Inorganic SOG)	16-18	425	1 hr
<b><u>Siloxanis</u></b> <b><u>Siloxanes</u></b> (Organic SOG)	2-13	425	1 hr
<u>Silicesquinoxanis</u> <u>Silsesquioxanes</u> (Organic SOG)	12	400	30 min
Hydrogen silicate (Inorganic SOG)	8	400	30 min
Hydrogen <u>silicesquinoxane</u> - <u>Silsesquioxane</u> (Inorganic SOG)	Less than 4	400	30-60 min